

CARPETING  
ROOFING  
ANIMAL FEED  
FERTILIZERS  
BUILDING MATERIAL

# CARBOCIA 310 Agri

Geldigheidsdatum : 01/01/2021 – 31/12/2021

**Site :** Vallée Heureuse – rue Henri Barbusse – Hydrequent (Rinxent)  
**Omschrijving :** **Grondstof voor de productie van diervoeding**  
**Calciumcarbonaat**




**Fysische eigenschappen :**  
Reële dichtheid 2,72 Mg/m<sup>3</sup>  
Bulkdichtheid 1,47 Mg/m<sup>3</sup>  
Vochtgehalte <1%

Stockering op propere en droge locatie  
Het lotnummer is de datum van levering

### Chemische eigenschappen :

	Gemiddelde	Limiet voor nemen actie	Limiet afwijzing	Limiet kennisgeving
<b>Oplosbare fluoride</b>	<b>27mg/kg</b>		< 350 mg/kg	< 350 mg/kg
<b>Kwik</b>	<b>&lt;0.01mg/kg</b>		< 0,3 mg/kg	< 0,3 mg/kg
<b>Arseen</b>	<b>0.6mg/kg</b>		< 15 mg/kg	< 15 mg/kg
<b>Lood</b>	<b>0.58mg/kg</b>		< 20 mg/kg	< 20 mg/kg
<b>Niet oplosbare as in HCl</b>	<b>&lt;5 g/100g</b>			< 5 g/100g
<b>Dioxines</b>	<b>0.0381</b>	0,5 ng/kg	<0,75 ng/kg	< 0,5 ng/kg
	<b>0.0585</b>		<1 ng/kg	< 1 ng/kg
	<b>0.0204</b>	0,35 ng/kg		0,35 ng/kg
	<b>0.0372</b>		< 10 µg/kg	< 10 µg/kg

### Granulometrische curve : gemiddelde waarden van 01/07/2020 tot 18/12/2020



tamis	0,063	0,125	0,2	0,5	1	2
Vss	<b>13</b>	<b>40</b>	<b>65</b>	<b>100</b>	<b>100</b>	<b>100</b>
Moy+1,25sf	11.82	31.97	56.34	96.33	100	100
Moy	10.31	28.37	50.76	91.38	100	100
Moy-1,25sf	8.80	24.77	45.19	86.42	100	100
Vsi	<b>3</b>	<b>15</b>	<b>35</b>	<b>75</b>	<b>98</b>	<b>99</b>
Nb d'essais	94	94	94	94	94	94

### Chemische samenstelling van het gesteente : gemiddelde waarden van 01/07/2020 tot 18/12/2020

CaCO <sub>3</sub>	CaO	Ca	Al <sub>2</sub> O <sub>3</sub>	MgO	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>
98.20	54.99	39.29	0.09	0.30	0.36	0.04

Kan worden gebruikt in de biologische landbouw en diervoeding volgens de Europese richtlijn UE N°505/2012 ( rectificatie van de richtlijn CE N°889/2008 )

The stated values and properties are the result of extensive development work, practical experience and accepted test methods. Our recommendations for application are supplied as a technical service. Carbocia retains the right to make changes to any data listed above to improve the products or their application. This data sheet supersedes all earlier technical data on this product.